

CDK Stone

4-6 Freighter Road Moorabbin VIC 3189 (03) 8552 6000

-Technical Data Sheet-

Product: CDK PolyPlus Water Clear Flowing
Material Class: Polyester System

1) Handling Properties

Mix Ratio: 100:2 resin to liquid hardener by weight
Gel Time at 21°C: 12-18 minutes
Cure Time at 21°C: 2-3 hours

2) Mechanical Properties

Shore D Hardness: 87
Tensile Strength: 9,000 psi
Flexural Strength: 12,000 psi
Compressive Strength: 19,000 psi
Cure Shrinkage: ~2%

3) Chemical Resistance

Water Absorption: < 0.5%
Salt (10%): Stable
Ammonia (10%): Stable
Hydrochloric Acid (10%): Not Tested
Acetic Acid (10%): Not Tested
Petroleum: Stable
Lubricating Oil: Stable

*** This data is provided for informational purposes only. Results based on tests performed by Superior Stone Products.***